SOCRATCES

CSP PROJECTS JOINT WEBINAR

CONCENTRATED SOLAR POWER PROJECTS

25th June 2021

SOCRATCES

MUSTEC
Market Uptake of Solar Thermal Electricity

NEXTOWER

SFERA

CSP
CONCENTRATED SOLAR POWER

SOCRATCES

Solar Calcium looping integRAtion for Thermo-Chemical Energy Storage

Politecnico di Torino · Universidad de Sevilla · EKETA Εθνικό Κέντρο Έρευνας & Τεχνολογικής Ανάπτυξης · Universidad Zaragoza · CSIC · calix · virtualmech virtual engineering. real results · BIOAZUL · ttz Bremerhaven · Aristotle University of Thessaloniki · spi Sociedade Portuguesa de Inovação · iSiTEC · Consiglio Nazionale delle Ricerche

Context

CSP main research lines

- **Cost reduction: equipment CAPEX and/or higher efficiencies**
- **Improving dispatchability**
  - **40%** of current CSP plants with thermal storage
  - CSP under development approx. **80%** with thermal storage
  - At commercial scale based on Molten salts or Ruth steam accumulators
- **Environmental sustainability**

ANDASOL I: 28,500 tons of molten salt. 60% sodium nitrate, 40% potassium nitrate. 1,010 MWh.

This Project has received funding from European Commission by means of Horizon 2020,the EU Framework Programme for Research & Innovation, under Grant Agreement no.727348.

SOCRATCES

Thermochemical Energy Storage Calcium-Looping (CaL)

Group	Example
Hydrogen systems $MH_n + \Delta H_r \leftrightarrow M + \left(\frac{n}{2}\right) H_2$	$MgH_{2\,(s)} + \Delta H_r \leftrightarrow Mg_{(s)} + H_{2\,(g)}$
Carbonate systems $MCO_{3\,(s)} + \Delta H_r \leftrightarrow MO_{(s)} + CO_{2\,(g)}$	$CaCO_{3\,(s)} + \Delta H_r \leftrightarrow CaO_{(s)} + CO_{2\,(g)}$
	$SrCO_{3\,(s)} + \Delta H_r \leftrightarrow SrO_{(s)} + CO_{2\,(g)}$
Hydroxide systems $M(OH)_{2\,(s)} + \Delta H_r \leftrightarrow MO_{(s)} + H_2O_{\,(g)}$	$Mg(OH)_{2\,(s)} + \Delta H_r \leftrightarrow MgO_{(s)} + H_2O_{\,(g)}$
	$Ca(OH)_{2\,(s)} + \Delta H_r \leftrightarrow CaO_{(s)} + H_2O_{\,(g)}$
Redox systems $M_xO_{y\,(s)} + \Delta H_r \leftrightarrow xM_{(s)} + \left(\frac{y}{2}\right) O_{2\,(g)}$	$2BaO_{2\,(s)} + \Delta H_r \leftrightarrow 2BaO_{(s)} + O_{2\,(g)}$
	$2Co_3O_{4\,(s)} + \Delta H_r \leftrightarrow 6CoO_{(s)} + O_{2\,(g)}$
Ammonia systems	$2NH_{3\,(g)} + \Delta H_r \leftrightarrow N_{2\,(g)} + 3H_{2\,(g)}$
Organic systems	$CH_{4(g)} + H_2O_{(l)} + \Delta H_r \leftrightarrow CO_{(g)} + 3H_{2\,(g)}$ With a side reaction: $CO_{(g)} + H_2O_{(l)} \leftrightarrow CO_{2\,(g)} + H_{2\,(g)} + \Delta H_r$
	$CH_{4(g)} + CO_{2\,(g)} + \Delta H_r \leftrightarrow 2CO_{(g)} + 2H_{2\,(g)}$ With a side reaction: $CO_{2(g)} + H_{2(g)} + \Delta H_r \leftrightarrow CO_{(g)} + H_2O_{\,(g)}$
Sulfur systems	$H_2SO_{4(g)} + \Delta H_r \leftrightarrow SO_{2(g)} + H_2O_{\,(g)} + \frac{1}{2} O_{2\,(g)}$

Calcium-Looping (CaL)

calcination

$$CaCO_{3\,(s)} \longrightarrow CaO_{(s)} + CO_{2\,(g)}$$

ΔH_r=+178 kJ/mol

carbonation

$$CaO_{(s)} + CO_{2\,(g)} \longrightarrow CaCO_{3\,(s)}$$

ΔH_r=-178 kJ/mol

This Project has received funding from European Commission by means of Horizon 2020,the EU Framework Programme for Research & Innovation, under Grant Agreement no.727348.

SOCRATCES

CSP-CaL Concept



R Chacartegui, A Alovisio, C Ortiz, JM Valverde, V Verda, JA Becerra, Thermochemical energy storage of concentrated solar power by integration of the calcium looping process and a CO_2 power cycle, Applied energy 173, 589-605

This Project has received funding from European Commission by means of Horizon 2020,the EU Framework Programme for Research & Innovation, under Grant Agreement no.727348.

CSP-CaL – Advantages and opportunities

1. High energy density





Technology	*Energy density [kWh/m³]*	*Maturity*
sensible	low	high
solid	↓	↑
liquid		
latent		
sorption		
thermochemical		
	high	low

Kuravi et al. (2013)

This Project has received funding from European Commission by means of Horizon 2020,the EU Framework Programme for Research & Innovation, under Grant Agreement no.727348.

SOCRATCES

CSP-CaL – Advantages and opportunities

2. Low-temperature energy storage

- ✓ Minimizes thermal losses
- ✓ Reduces parasitic consumption of auxiliaries
- ✓ Capacity for seasonal storage
- ✓ Increases capacity factor

Molten salts → T min Storage ~200ºC



CO2 storage



Different solids storage strategies



This Project has received funding from European Commission by means of Horizon 2020,the EU Framework Programme for Research & Innovation, under Grant Agreement no.727348.

CSP-CaL – Advantages and opportunities

3. Abundant and stable materials→ limestone, dolomite, etc.

Low-price



Abundant and widely available

Non-hazardous or contaminant

Characteristics for the large scale deployment of an energy storage system

This Project has received funding from European Commission by means of Horizon 2020,the EU Framework Programme for Research & Innovation, under Grant Agreement no.727348.

CSP-CaL – Advantages and opportunities



4. High temperature exothermic reaction

- ✓ Energy delivery at high temperature 650-1000ºC as a function of CO_2 partial pressure
- ✓ An advantage compared with molten salts →T máx ~550-600°C due to salts degradation
- ✓ Integration of high-efficiency power cycles





This Project has received funding from European Commission by means of Horizon 2020,the EU Framework Programme for Research & Innovation, under Grant Agreement no.727348.

SOCRATCES

CSP-CaL – Advantages and opportunities



5. Direct and indirect integration of power cycles

- ✓ Flexibility for design and operation
- ✓ Based on the high temperature of the reaction

Direct (Recuperative Brayton CO2)



Indirect



C Ortiz, R Chacartegui, JM Valverde, A Alovisio, JA Becerra, **Power cycles integration in concentrated solar power plants with energy storage based on calcium looping**, Energy Conversion and Management 149, 815-829 2017

This Project has received funding from European Commission by means of Horizon 2020,the EU Framework Programme for Research & Innovation, under Grant Agreement no.727348.

CSP-CaL – Advantages and opportunities



6. Materials y equipment used at an industrial scale

- Proximity with cement industry
- Calciner (solar integration)
- Entrained flow reactors
- Closed CO2 Brayton cycle
- Solids transport
- Cyclons
- Storage tanks



BAT for cement industry (2013)



Arias et al. (2013)

This Project has received funding from European Commission by means of Horizon 2020,the EU Framework Programme for Research & Innovation, under Grant Agreement no.727348.

Main Challenges

1. Solar calciner. High-temperature receivers



i) Particles residence time

ii) Particles circulation within the system

iii) Closed CO_2 loop operation

iv) Thermal gradients control

v) Continuous operation for scaling up

Particles solar receivers High-temperature

This Project has received funding from European Commission by means of Horizon 2020,the EU Framework Programme for Research & Innovation, under Grant Agreement no.727348.

Main Challenges



Alternatives for reducing the calcination temperature

Steam calcination

- Commercial availability
- Closeness to CSP tower
- Separation condensing
- **Effects on particles structure**



Helium calcination



- Reduced loss of activity with cycles
- **Membranes separation**

Vacuum calcination



This Project has received funding from European Commission by means of Horizon 2020,the EU Framework Programme for Research & Innovation, under Grant Agreement no.727348.

Main Challenges

2. Multicyclic CaO conversion

$$CaO_{(s)} + CO_2 \rightarrow CaCO_{3(s)} \qquad \Delta H_r^0 = -179,2 \frac{kJ}{mol}$$

Deactivation with the number of cycles

It affects to plant performance

$$X = \frac{mol\ CaO\ reacted}{mol\ CaO\ in} = \frac{mol\ CaCO_3\ produced}{mol\ CaO\ in}$$

$$CO_2\ captured = CaCO_3\ formed = CaO \cdot X$$

$$(1 - X) = solids\ inerts$$ → **Efficiency penalty**

Deactivation is highly dependent on the design conditions of reactors, material and processes





B Sarrión, A Perejón, PE Sánchez-Jiménez, N Amghar, R Chacartegui, ..., Calcination under low CO2 pressure enhances the calcium Looping performance of limestone for thermochemical energy storage, Chemical Engineering Journal, 127922,2020



This Project has received funding from European Commission by means of Horizon 2020,the EU Framework Programme for Research & Innovation, under Grant Agreement no.727348.

Summary of main benefits of CaL Storage concept (SOCRATCES)

1 CaO precursors:

- ✓ Low price
- ✓ wide availability
- ✓ harmlessness

2 Carbonation for generating heat ~650-1000ºC

- ✓ High efficient generation of electricity

3 Reactants and products can be stored at ambient temperature

Ambient temperature

4 High energy density to maximize storage capacity



5 Materials and process equipment

- ✓ Well-known in the cement industry

This Project has received funding from European Commission by means of Horizon 2020,the EU Framework Programme for Research & Innovation, under Grant Agreement no.727348.

SOCRATCES operation conditions



Figure 1: Schematic representation of SOCRATCES.



Figure 2. Calcination-carbonation reaction equilibrium



This Project has received funding from European Commission by means of Horizon 2020,the EU Framework Programme for Research & Innovation, under Grant Agreement no.727348.

Material behauviour under SOCRATCES operation conditions



SOCRATCES CSP conditions

CO_2 capture conditions

Figure 1: The humble limestone and dolomite show high residual conversion (Xr) at SOCRATCES conditions

This Project has received funding from European Commission by means of Horizon 2020,the EU Framework Programme for Research & Innovation, under Grant Agreement no.727348.

Objectives.

- SOCRATCES global objective is to **advance in the knowledge of the Calcium Looping (CaL) for thermochemical energy storage (TCES)**.

- The project **develops prototypes of the different components and implements their integration in order to reduce the core risks of scaling up** TCES-CaL technology, to identify and to solve challenges; to advance in the understanding of the processes and to optimize the performance of components and global systems with the longer-term goal of enabling highly competitive and sustainable TCES-CSP plants integrating the TCES-CaL technology.

- SOCRATCES is oriented to **generate new knowledge** about the whole CaL process: equipment, materials, reactions, transport, etc. in order **to identify and solve the challenges** for the development of the TCES-CaL system at a commercial scale of MWs.

This Project has received funding from European Commission by means of Horizon 2020,the EU Framework Programme for Research & Innovation, under Grant Agreement no.727348.

SOCRATCES

New materials

R & D

Reactions (Ch/Ph)

Scaling-Up **A**ssessment



Systems integration & control

Engineering Construction

Systems development

Power Systems technologies

This Project has received funding from European Commission by means of Horizon 2020,the EU Framework Programme for Research & Innovation, under Grant Agreement no.727348.

SOCRATCES

SOCRATCES Prototypes. First of their kinds

Secondary reflector/reactor

Solar cyclone calciner

Downer gravity closed loop calciner





Downer closed loop carbonator





This Project has received f rom European Commission
by means of Horizon 2020,the EU Framework Programme for
Research & Innovation, under Grant Agreement no.727348.



SOCRATCES

This Project has received funding from European Commission by means of Horizon 2020,the EU Framework Programme for Research & Innovation, under Grant Agreement no.727348.



CaO (s)
CaO storage
CaO (s)
CALCINER
$CaCO_{3(s)} \rightarrow CaO_{(s)} + CO_{2(g)}$
Q
HEAT EXCHANGER NETWORK
CaCO₃/CaO storage
HEAT EXCHANGER NETWORK
CARBONATOR
$CaO_{(s)} + CO_{2(g)} \rightarrow CaCO_{3(s)}$
POWER CYCLE
Q
CO2 TUR
CO₂ storage
CO2 (g)
Carga de energía
Almacenamient
Descarga/producci
SOCRATCES
This Project has recei
by means of Horizon 2
Research & Innovatio
TCES





This Project has received funding from European Commission by means of Horizon 2020,the EU Framework Programme for Research & Innovation, under Grant Agreement no.727348.

https://socratces.eu/

https://www.linkedin.com/company/socratces/

SOCRATCES

Published results, analysis, data (a non complete sample)

Integrations and processes

- R Chacartegui, A Alovisio, C Ortiz, JM Valverde, V Verda, JA Becerra, **Thermochemical energy storage of concentrated solar power by integration of the calcium looping process and a CO2 power cycle,** Applied energy 173, 589-605 First publication
- A Alovisio, R Chacartegui, C Ortiz, JM Valverde, V Verda, **Optimizing the CSP-calcium looping integration for thermochemical energy storage**, Energy Conversion and Management 136, 85-98 2017 Seasonal storage
- C Ortiz, MC Romano, JM Valverde, M Binotti, R Chacartegui, **Process integration of Calcium-Looping thermochemical energy storage system in concentrating solar power plants**, Energy 155, 535-551 2018 Hot storage
- C Ortiz, R Chacartegui, JM Valverde, A Alovisio, JA Becerra, **Power cycles integration in concentrated solar power plants with energy storage based on calcium looping**, Energy Conversion and Management 149, 815-829 2017 Power cycles analysis
- C Ortiz, M Binotti, MC Romano, JM Valverde, R Chacartegui, **Off-design model of concentrating solar power plant with thermochemical energy storage based on calcium-looping**, AIP Conference Proceedings 2126 (1), 210006 2019 Off design

Materials

- C Ortiz, JM Valverde, R Chacartegui, LA Perez-Maqueda, **Carbonation of limestone derived CaO for thermochemical energy storage: from kinetics to process integration in concentrating solar plants**, ACS Sustainable Chemistry & Engineering 6 (5), 6404-6417 2018 Scales impact
- C Ortiz, JM Valverde, R Chacartegui, **Energy Consumption for CO2 Capture by means of the Calcium Looping Process: A Comparative Analysis using Limestone, Dolomite, and Steel Slag**, Energy Technology 4 (10), 1317-1327 Effect of different materials

  Biomineralized materials
- J Arcenegui-Troya, PE Sánchez-Jiménez, A Perejón, JM Valverde, ...**Calcium-Looping Performance of Biomineralized CaCO3 for CO2 Capture and Thermochemical Energy Storage**, Industrial & Engineering Chemistry Research 59 (29), 12924-12933, 2020 Biominerals
- B Sarrión, A Perejón, PE Sánchez-Jiménez, N Amghar, R Chacartegui, ..., **Calcination under low CO2 pressure enhances the calcium Looping performance of limestone for thermochemical energy stora**ge, Chemical Engineering Journal, 127922,2020 Low-Pressure Calcination

This Project has received funding from European Commission by means of Horizon 2020,the EU Framework Programme for Research & Innovation, under Grant Agreement no.727348.

SOCRATCES

Published results, analysis, data (a non complete sample)

Components

- B Sarrión, A Perejón, PE Sánchez-Jiménez, N Amghar, R Chacartegui, ..., **Calcination under low CO_2 pressure enhances the calcium Looping performance of limestone for thermochemical energy storage**, Chemical Engineering Journal, 127922,2020

Calciner Effect of Low pressure calcination

- U Tesio, E Guelpa, C Ortiz, R Chacartegui, V Verda, **Optimized synthesis/design of the carbonator side for direct integration of thermochemical energy storage in small size Concentrated Solar Power**, Energy Conversion and Management: X 4, 100025, 2019

Carbonator

CaL Perspectives and challenges

- C Ortiz, JM Valverde, R Chacartegui, LA Pérez-Maqueda, ..., **Scaling-up the Calcium-Looping Process for CO_2 Capture and Energy Storage**, KONA Powder and Particle Journal 38, 189-208, 2021
- C Ortiz, JM Valverde, R Chacartegui, LA Perez-Maqueda, P Giménez, **The calcium-looping ($CaCO_3$/CaO) process for thermochemical energy storage in concentrating solar power plants**, Renewable and Sustainable Energy Reviews 113, 109252 2019

Reviews

Hybrid CaL CSP/PV

- R Bravo, C Ortiz, R Chacartegui, D Friedrich, **Multi-objective optimisation and guidelines for the design of dispatchable hybri solar power plants with thermochemical energy storage**, Applied Energy 282, 116257, 2021

Data clustering

- R Bravo, C Ortiz, R Chacartegui, D Friedrich, **Hybrid solar power plant with thermochemical energy storage: A multi-objectiv operational optimization**, Energy Conversion and Management 205, 112421, 2020

Optimization operation

- R Fernández, C Ortiz, R Chacartegui, JM Valverde, JA Becerra, **Dispatchability of solar photovoltaics from thermochemical energy storage**, Energy Conversion and Management 191, 237-246 2019

Concept

CaL Combined Cycle

- C Ortiz, R Chacartegui, JM Valverde, A Carro, C Tejada, J Valverde , **Increasing the solar share in combined cycles through thermochemical energy storage,** , Energy Conversion and Management 229, 113730, 2021

This Project has received funding from European Commission by means of Horizon 2020,the EU Framework Programme for Research & Innovation, under Grant Agreement no 727348

Novel Concept. More recent approach. An alternative pathway?

SOCRATCES

SOCRATCES

Solar Calcium looping integRAtion for Thermo-Chemical Energy Storage

THANK YOU FOR YOUR ATTENTION

https://socratces.eu/

Politecnico di Torino · Universidad de Sevilla · EKETA · CSIC · virtualmech · Universidad Zaragoza · calix · BIOAZUL · ttz Bremerhaven · Aristotle University of Thessaloniki · spi Sociedade Portuguesa de Inovação · ISITEC · Consiglio Nazionale delle Ricerche

SOCRATCES

Solar Calcium looping integRAtion for Thermo-Chemical Energy Storage

Politecnico di Torino · Universidad de Sevilla · EKETA · CSIC · virtualmech · Universidad Zaragoza · calix · BIOAZUL · ttz Bremerhaven · Aristotle University of Thessaloniki · spi Sociedade Portuguesa de Inovação · iSiTEC · Consiglio Nazionale delle Ricerche

SOCRATCES

Thanks for your attention

This Project has received funding from European Commission by means of Horizon 2020,
the EU Framework Programme for Research & Innovation, under Grant Agreement no.727348.